

### Protac™ High Gloss

Overlaminating Film

Protac™ High Gloss is a 4 mil (100µ) clear PET laminating film with a high gloss finish, coated on one side with a pressure sensitive, solvent acrylic adhesive that is protected by a one side siliconized PET release liner.

#### Typical Applications

- Adds depth and detail to any image, whether it is photographic, inkjet or other output media.
- Ideal for photographic prints, photo albums, POP displays, or anywhere a high gloss finish is desired.

#### Product Structure

Film	High Gloss PET	5 mil (125µ)
Adhesive	Solvent Acrylic (Pressure Sensitive)	
Release Liner	Siliconized 1 Side PET	

#### Physical Characteristics

Film Thickness	4 mil (100µ)
Adhesive Layer	1 mil (25µ)
Film/Adhesive Ratio	4:1
UV Protection Factor	Not Applicable
Outdoor Durability	1 year
Service Temperature Range	-4°F to 230°F (-20°C to 110°C)
Peel Strength (20 min, FTM1)	14.7 N/25mm
Shelf Life	Use within 1 year after opening original box
Storage Conditions	59°F to 72°F (15°C to 22°C); 50 - 55% Relative Humidity

#### Process Settings

Equipment Type	Temperature	Speed
Roller Laminator	Room temperature to 104°F (40°C)	1 ft to 8 ft (0.3m to 2.5m) per minute
Press	Not recommended	

#### IMPORTANT NOTE:

Information is intended only as a guide and is given without guarantees. We strongly recommend a preliminary test of printing and curing on the substrates intended for use, in order to ascertain exactly the procedure, the working times and the obtained affect. Follow the indications on the package, ask for the safety data sheets and always follow the indications contained therein.

Only the correct use of the product will allow satisfactory results. For this reason, Drytac is not responsible for improper use of the product, either by application or substrate applied to. Make certain that product is right for the desired use, and work according to the instructions given in our technical data sheets. If in doubt of the appropriate application methods or use, contact Drytac at one of the phone numbers listed below.