

MultiTac[™]

Mounting Adhesive

MultiTac[™] is a high quality PET film, coated on both sides with a pressure sensitive, high tack acrylic adhesive, one of which is protected by fine paper coated on both sides with siliconized PE. The adhesive is self-wound on the release liner. A clear and white version are available.

Typical Applications

- Suitable for image decal and high-volume mounting of graphics onto difficult substrates, such as Forex[™], MDF, Gatorboard[™], Ultraboard[™], Foamex[™], or Sintra[™].
- The white version of MultiTac[™] offers excellent opacity and the ability to mount to dark substrates.

Process Settings

Equipment Type	Temperature	Speed
Roller Laminator	Room temperature to 120°F (49°C)	1 ft to 8 ft (0.3m to 2.5m) per minute
Press	Not recommended	

Product Structure

	MultiTac [™] Clear	MultiTac [™] White
Adhesive	Acrylic (Pressure Sensitive)	Acrylic (Pressure Sensitive)
Film	Clear PET	White PET
Adhesive	Acrylic (Pressure Sensitive)	Acrylic (Pressure Sensitive)
Release Liner	2 Side PE Coated, 2 Side Siliconized Fine Paper	2 Side PE Coated, 2 Side Siliconized Fine Paper

Physical Characteristics

	MultiTac [™] Clear	MultiTac [™] White
Adhesive Layer	1.2 mil (30µ) on each side	
Adhesive pH	6.0	
Service Temperature Range	-22°F to 284°F (-30°C to 140°C)	
180° Peel (ozf/in)	67	
Shelf Life	Use within 1 year after opening original box	
Storage Conditions	59°F to 72°F (15°C to 22°C); 50 - 55% Relative Humidity	

IMPORTANT NOTE:

Information is intended only as a guide and is given without guarantees. Purchasers should independently determine, prior to use, the suitability of each material for their specific purpose. Follow the indications on the package, ask for the safety data sheets and always follow the indications contained therein. Only the correct use of the product will allow satisfactory results. For this reason, Drytac is not responsible for improper use of the product, either by application or substrate applied to. Make certain that product is right for the desired use, and work according to the instructions given in our technical data sheets. If in doubt of the appropriate application methods or use, contact Drytac at one of the phone numbers listed below.